



# WET-STICK THERMOPLASTIC

PRODUCT CODE: 255

## DESCRIPTION

DEWITT'S WET-STICK THERMOPLASTIC is an all-purpose patching cement Originally designed for Single-Ply roofing systems, but it can also be used on all roofing systems. Our manufacturing process utilizes specially blended Thermoplastic Resins refined oils, and mineral stabilizers and reinforced with hi-tech asbestos free fibers. DEWITT'S WET-STICK THERMOPLASTIC sets up to form a tough, continuous, moisture-free film that will retain its pliability for a long period of time. This enables it to expand and to conform to movement of other materials. DEWITT'S WET-STICK THERMOPLASTIC can be used on wet or dry surfaces.

## USES

DEWITT'S WET-STICK THERMOPLASTIC is an excellent all-purpose cement for repairs of all flashings and is ideal for vertical surface application around roofs, parapet walls, chimneys, valleys, pipes and foundations. DEWITT'S WETSTICK THERMOPLASTIC can also be used for repairing leaks in EPDM, TPO, HYPALON, METAL, Concrete, Wood and ASPHALT ROOFS

## APPLICATION

DEWITT'S WET-STICK THERMOPLASTIC is used directly from the container. **DO NOT THIN.** Apply with a trowel or putty knife to surface that must be free of dirt, dust, and debris. For flashings, apply 1/8"-1/2" thick and trowel it down to a smooth feather edge. On thick applications reinforce area with membrane. For patching, apply DEWITT'S WET-STICK THERMOPLASTIC over area 3/8"-1/2" thick. Application on wet surfaces requires THERMOPLASTIC to be worked into surface with some pressure for best results. Over application on EPDM Roofs may cause some swelling of the EPDM.

## SPECIFICATIONS

Meets ASTM D2370 and ASTM D2939

## COVERAGE

1 gallon covers approximately 7sq. ft. at 1/4" thick

## PACKAGING

2.8 gallon, .9 gallon

## CAUTION

**Combustible:** Keep away from heat and open flame. Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed.



## PHYSICAL CHARACTERISTICS

WEIGHT PER GAL (APPROX.)	9 lbs
FLASH POINT (ASTM 093-52)	100° F Min
DRYING TIME	2-3 days, depending on weather
VISCOSITY AT 80° F	Light to Medium Trowel
SERVICE TEMPERATURE (EXTENDED EXPOSURE)	-40° to 180° F
RESISTANCE TO OILS AND SOLVENTS	Poor
RESISTANCE TO SUNLIGHT AND CHEMICALS	Excellent
EFFECTS OF WEATHERING	Minimal
WATER RESISTANCE	
UNDER DRAINING CONDITIONS	Excellent
UNDER CONTINUOUS SUBMERSION	Fair
CLEAN UP	Mineral Spirit or DEWITT'S REMOVE-IT
APPLICATION TEMPERATURE	25°-100° F