

**Quality Since** 

# SILVER SHIELD 200 ALUMINUM ROOF COATING

## DESCRIPTION

DEWITT'S SILVER SHIELD 200 ALUMINUM ROOF COATING is a solvent type, asphalt based coating that is similar to conventional roof coatings. Manufactured with special blend asphalts, refined oils, mineral stabilizers, and reinforced with hi-tech asbestos-free fibers. Aluminum coatings provide a tough continuous coating with extra-long life and good initial brightness. Aluminum pigment gives it a bright, metallic aluminum color when applied on metal, tile, conventional bituminous roof surfaces and modified bitumen. This reflective coating reduces the deteriorating effect of the sun's rays, reduces interior temperature, and protects roof surfaces from excessive weathering.

#### USES

DEWITT'S SILVER SHIELD 200 can be used on old asphalt roofs, smooth or mineral surfaced, silos, metal roofs and siding, water towers, modified bitumen, mobile homes, campers, and R.V.'s. Aluminum coatings can reduce interior temperatures up to 15°F and serve as a rust inhibitor and anti-corrosive agent.

#### **APPLICATION**

Surfaces must be dry, and free of dirt, dust, and debris. Dried out roofs should be primed with DEWITT'S ASPHALT PRIMER (#154). Repair all cracks, breaks, or open seams with DEWITT'S PRO FLASH ROOF CEMENT (#251). Do not apply when rain appears imminent or less than four hours before surface can be expected to be covered with dew. DEWITT'S SILVER SHIELD 200 is ready to use from the container. Moderate stirring is required to mix pigment. Stir after each application. Apply with roof brush, squeegee, or spray gun. When brushing, brush last strokes all one way.

#### **SPECIFICATIONS**

Meets Federal Specification TT-C-498C, ASTM D-2824-85, Type III, except this material is asbestos free. Pigment Specification ASTM D-962. Contains 2 lbs. of aluminum paste per gallon.

#### COVERAGE

2 gallons per 100 sq. ft. on roofing felts and masonry. 1.5 gallons per 100 sq. ft. on metal.

#### PACKAGING

55 gallon drum & 5 gallon pails

### **CAUTION**

Combustible: Keep away from heat and open flame. Close container after each use. Keep out of reach of children. Do not induce vomiting. Harmful if swallowed.



# **PHYSICAL CHARACTERISTICS**

| WEIGHT PER GAL (APPROX.)                                                     | 8lbs                                                                                              |
|------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------------|
| FLASH POINT (ASTM 093-52)                                                    | 100° F Min                                                                                        |
| DRYING TIME                                                                  | 8 hours Min                                                                                       |
| VISCOSITY AT 80° F                                                           | 35 sec                                                                                            |
| SERVICE TEMPERATURE (EXTENDED<br>EXPOSURE)                                   | -20° to 180° F                                                                                    |
| RESISTANCE TO OILS AND SOLVENTS                                              | Poor                                                                                              |
| RESISTANCE TO SUNLIGHT AND CHEMIC                                            | CALS Excellent                                                                                    |
| WATER RESISTANCE<br>UNDER DRAINING CONDITIONS<br>UNDER CONTINUOUS SUBMERSION | Excellent<br>Poor                                                                                 |
| CLEAN UP                                                                     | Mineral Spirit or Naphtha                                                                         |
| APPLICATION TEMPERATURE                                                      | 25°-100° F (formulated for seasonal<br>use:<br>summer grade, fall/<br>spring grade, winter grade) |

#### RESTRICTIONS

Do not use on dead level asphalt, tar base, or gravel roofs. Concrete surfaces must be primed with DEWITT'S ASPHALT PRIMER (#154). Freshly coated hot bituminous roofs should be allowed to weather at least 3 months. Roofs patched or primed should weather at least 10 days. Modified bitumen roofs should weather 30-90 days before application.

DeWitt Products Company | 5860 Plumer St, Detroit, MI 48209 Phone: (313) 554 - 0575 | Fax: (313) 554 - 2171 www.dewittproducts.com

